

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C08F 4/64, 10/06</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/52950</b> <b>(43) International Publication Date:</b> 21 October 1999 (21.10.99)
<b>(21) International Application Number:</b> PCT/EP99/02378 <b>(22) International Filing Date:</b> 8 April 1999 (08.04.99)  <b>(30) Priority Data:</b> 198 16 154.9      9 April 1998 (09.04.98)      DE  <b>(71)(72) Applicant and Inventor:</b> RIEGER, Bernhard [DE/DE]; Johann-Stockar-Weg 50, D-89075 Ulm (DE).  <b>(74) Agent:</b> PFENNING, MEINIG & PARTNER GBR; Mozart- strasse 17, D-80336 München (DE).		<b>(81) Designated States:</b> AL, AU, BA, BB, BG, BR, CA, CN, CU, CZ, EE, GD, GE, HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, US, UZ, VN, YU, ZA, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> A CATALYST COMBINATION AND A PROCESS FOR PREPARING LINEAR, ISOTACTIC POLYMERS  <b>(57) Abstract</b>  The invention concerns a catalyst combination for preparing linear isotactic polymers, wherein said catalyst combination contains a metal complex and an activator and a process for preparing linear, isotactic polymers which have a structure of which the tacticity varies within the range of between 25 and 60 % of [mmmm] pentad concentration, an arbitrary or rather regular sequence of isotactic and atactic blocks being excluded, in which process a C <sub>2</sub> to C <sub>20</sub> olefin are reacted with the catalyst combination.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

A Catalyst Combination and a Process for Preparing  
Linear, Isotactic Polymers

5 The present invention relates to a new catalyst combination and a process for preparing linear, isotactic polymers, wherein the isotacticity of the linear polymers due to a statistic distribution of stereoscopic errors in the polymer chain, being within the range of from 25 to 60 % of [mmmm] pentad concentration.

10 For a long time, isotactic polymers have been of interest as plastic materials for manufacturing articles of relatively good deformation resistance, such as e.g. sheathings of household appliances. In general, such isotactic polymers with propylene as  
15 monomer are of highly crystalline nature and, therefore, relatively hard with little or no impact resistance at all so that they will come into question only for application fields in which those characteristics are desirable.

Most recently, various attempts have been made, aiming at preparing also polypropylene with elastic characteristics. European Printed Publication 0 707 016 A1 specifies a catalyst composition and a process for preparing polyolefins. The catalysts specified in European Printed Publication 0 707 016 A1 are, in substance, made up of a metallocene compound having an indene ring and a fluorene ring which are bridged via C, Si or Ge. In case of the metallocene compound, it, in this connexion, is obviously essential that, in the indene ring system, at least the residue denoted with R<sup>4</sup> not be hydrogen. When that residue R<sup>4</sup> is hydrogen, the effects, such as specified in the aforementioned European Patent Application, will not be attained (P 6, from L 57 up to P 7, L 3). The polymers specified in European Printed Publication 0 707 016 A1 and prepared with metallocenes, here especially the polypropylene prepared with those metallocenes, however, show as can be drawn from the examples and the graphs, but unsatisfactory characteristics in regard of the elastic behaviour.

Departing from all these facts, it is the object of the present invention to find a new catalyst combination and to suggest a process to make polymers from olefinically unsaturated compounds available, not only showing thermoplastic but, at the same time, thermoplastic-elastic characteristics and, thus, being applicable for many application fields.

That object is, in regard of the catalyst combination, solved by the characterising features of Claim 1; in regard of the process for preparing the polymers, it is solved by the characterising features of Claim 5.


The invention relates to a new catalyst combination containing a metal complex and an activator.

The metal complex is a metallocene compound.

Herewith, metal compounds of the Fourth Auxiliary Group of the Periodic System Table IVB generally come into question, which compounds may be present as defined metal complexes and with which compounds activators are mixed. In general, the metals are present in the complexes in formally positively charged manner.

As regards the metals, titanium, zirconium, hafnium, vanadium, niobium, and tantalum specifically come into question, the metal atom preferably showing halogen or a C<sub>1</sub> - C<sub>8</sub> alkyl, aryl or benzyl as residue X.

The metallocene is defined by general Formula I.




wherein the residues R<sup>1</sup> - R<sup>7</sup> are a linear or branched C<sub>1</sub> - C<sub>10</sub> alkyl, a 5-7-linked cycloalkyl that, in its turn, may carry one or several C<sub>1</sub> - C<sub>8</sub> alkyl residues as substituents, a C<sub>6</sub> - C<sub>10</sub> aryl, aryl alkyl or alkyl aryl, in which case R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup>, and R<sup>5</sup>, R<sup>6</sup>, R<sup>7</sup>, here again, may be partially or simultaneously integrated

into 5-7-linked cycloalkyl or aryl rings fused thereto.

5 In case of the metallocene compound according to general Formula I, it is essential that, in general Formula I, the carbon atom adjacent to the residue R<sup>7</sup> and the carbon atom adjacent to the residue R<sup>6</sup> be, with the indene ring system, only hydrogen. Thereby, it is ensured that, with the indene ring system, a linear system can form by the residues R<sup>6</sup> and R<sup>7</sup>, which system, obviously, will prove to be especially  
10 advantageous when preparing the isotactic elastomers according to the invention. In contrast to the metallocene complex according to European Printed Publication 0 707 016 A1, only hydrogen atoms and no  
15 carbon atoms with further residues, as is imperative in the aforementioned European laying-open specification, can, thus, be found at the positions mentioned in the foregoing.

20 In this connexion, suitable bridging structural units E are 1.2-ethyl, 1.3-propyl, 1.4-butyl, carbon, silicon or germanium. For the case that E is carbon, silicon or germanium, the bridging structural unit E may, herewith, additionally carry the residues R<sup>9</sup> and R<sup>10</sup> which, then, are a C<sup>1</sup> - C<sub>8</sub> alkyl, a 4-7-linked  
25 cycloalkyl or aryl, R<sup>9</sup> and R<sup>10</sup> being able to also form a 4-7-linked cycloalkyl or aryl jointly with E.

A particularly preferred embodiment of the invention resides in that such a metallocene complex is used as reflected by general Formula VII.




wherein all the residues have the significations indicated above. In contrast to the metallocene complex according to general Formula I, it, however, now is imperative here on the indene ring system that another ring fused thereto be at hand which is bridged via two  $E^2$  groups.

$E_2$  therewith, signifies  $CH_2$ , oxygen or sulphur and  $n$  is 1 or 2.

As defined in Patent Claim 1, it certainly is furthermore provided in accordance with the invention, to additionally use at least also one activator, apart from the metallocene compounds specified above. The invention, herewith, generally encompasses all the activators that have as yet become known in the state-of-the-art for metallocene compounds. Such activators have also been specified by European Printed Publication 0 707 016 A1. As activator, at least one compound of general Formulas II to VI is, however, used with special preference. Accordingly, the activator may be an open-chain or



cyclic alumoxane compound of general Formula II or III, such as is reflected hereinafter:




5

wherein  $\text{R}^8$  is a  $\text{C}_1 - \text{C}_4$  alkyl group and  $n$  is a number between 5 and 30.

In case of the catalyst combination according to the invention, also the above-specified compounds of general Formulas II and III can, alone or in combination with the subsequent activators such as are reflected by general Formulas IV to VI, be used.

10



15

In general Formulas IV to VI,  $\text{R}^9$ , in this connexion, signifies a  $\text{C}_1 - \text{C}_4$  alkyl group or an aryl group.

20

It has, therewith, proven to be especially favourable when the metallocene complex according to general Formula I and the activator according to general Formulas II to VI are employed in such quantities that the atomic ratio between aluminium from the alumoxane or boron from the cationic activator and the transition metal from the metallocene complex is within the range of from 1:1 to  $10^6:1$ .

25

The invention furthermore relates to a process for preparing linear, thermoplastic-elastic polymers from olefinically unsaturated compounds with an isotactic arrangement of the monomer unit and a statistic distribution of isolated stereoscopic errors along the

individual chains, tacticity varying within the range of between 25 and 60 % [mmmm] pentad concentration. A regular sequence of isotactic and atactic blocks, therewith, is excluded. In many cases, it was found that the [rmrm] pentad was totally missing or present with a maximum of 2.5 % of the entire pentad area. Furthermore, it became evident that, in most cases, the [rrrr] and [rrrm] pentads are always greater than the [rmrm] pentad. The process according to the invention is specifically characterised in that a specially selected catalyst combination is used as described before.

Pressures of from 1 to 100 bars, preferably of from 3 to 20 bars and in particular of from 5 to 15 bars, have proven to be suitable reaction parameters for preparing the linear, thermoplastic, elastomeric olefin polymers. Favourable temperatures are within the range of from -50 °C to 200 °C, of preference at from 100 to 150 °C and of high preference at from 20 to 50 °C.

The polymerisation reactions can be carried out in the gas phase, in suspension and in supercritical monomers and especially in solvents inert under polymerisation conditions. In particular the solution polymerisation has proven to be the clearly superior thing for the present preparation process. Suitable inert solvents for that purpose are such solvents that do not contain any reactive groups in the molecule, i. e. aromatic solvents like benzole, toluol, xylol, ethyl benzole or alkanes such as e. g. propane, n-butane, i-butane, pentane, hexane, heptane or mixtures thereof.

The polymers prepared according to the invention are linear, thermoplastic, elastic polymers from an

olefinically unsaturated compound with an isotactic arrangement of the monomer units and a statistic distribution of isolated stereoscopic errors along the individual chains and a mean molecular weight Mw of the polymers within the range of from 100,000 to 800,000 gms/mol and a TG of from -50 to +30.

With the polymer prepared according to the invention, it is essential that the stereoscopic errors be situated in the polymer chain itself and that, thus, a specific pentad concentration result. In this connexion, it was found that, with the polymers prepared according to the invention, the [rmm] pentad with a maximum of 2.5 % of the entire pentad area will, in general, be present. In many cases, it was also found that that [rmm] pentad was completely missing.

Furthermore, it became evident that, in most cases, the [rrrr] and [rrrm] pentads are always greater than the [rmm] pentad. Determination of the pentad concentration in case of polymers has, properly speaking, become known from the state-of-the-art and is specified e.g. in J. A. Ewen, "Catalytic Polymerisation of Olefins", Eds. T. Keii, K. Soga; Kodanska Elsevier Pub.; Tokyo, 1986, P 271 et seqq. Also the pentad concentration determination according to the invention now present was carried out by means of the method specified in the above-mentioned piece of pertinent literature.

Apart from the above-mentioned specific pentad concentration, the linear, isotactic polymers have a molecular weight within the range of from 100,000 to 800,000, of preference from 110,000 to 500,000 and of special preference within the range of from 120,000 to 300,000 gms/mol. The mean molecular weights Mw

(mean weight value) of the polymers were measured by means of the gel permeation chromatography (GPC) method at 135 °C with microstyrigel as column material and 1, 2, 4-trichlorobenzole as solvent against closely distributed polypropylene standards. The molecular weight distribution Mw/Mn (mean weight value/mean numerical value) of the polymers was likewise measured by means of the gel permeation chromatography method and generally amounts to from 1.2 to 3.5.

In addition to all that, the polymers show a glass transition temperature Tg within the range of from -50 °C to +30 °C, of special preference a Tg of from -20 °C to +10 °C. The glass transition temperature was determined by means of the DSC method.

The linear, isotactic polymers prepared according to the invention present, after all, a structure of one or several C<sub>2</sub> - C<sub>20</sub> olefins. In this case, the olefin is preferred to be a C<sub>3</sub> - C<sub>20</sub> - Alk-1-ene. Examples of such C<sub>3</sub> - C<sub>20</sub> - Alk-1-enes are: propene, 1-butene, 2-butene, 1-pentene, 1-hexene, 1-octene, 1-nonene, 1-decene, 1-dodecene, 1-hexadecene, 1-octadecene, 1-eicosene.

Apart from the already mentioned olefins, also C<sub>5</sub> - C<sub>20</sub> cycloolefins are of the especially suitable kind. Examples thereof are cyclopentene, cyclohexene, norbornadiene and its derivatives.

In case of the linear, isotactic polymers, polypropylene is especially preferred. Further suitable polymers are copolymers from propylene and a C<sub>4</sub> - C<sub>20</sub> olefin or a cycloolefin. It is also possible to prepare terpolymers which show the characteristics defined in Patent Claim 1 when they present a

structure of propylene, a C<sub>2</sub> - C<sub>20</sub> olefin and a cycloolefin.

The polymers prepared according to the invention are e.g. soluble in toluol at a temperature within the range of from 20 to 80 °C; they show a distinct elastic behaviour in a tensile-strength test, measured with a "Standard Universal Testing Machine ZWICK 1445", as specified in the examples, and, in general, possess a crystallisation melting temperature, measured by means of the "Differential Scanning Calometry" (DSC) method within the range of from -50 °C to 150 °C. In particular, it has to be emphasised that, also in this case, the polymers clearly differ, in regard of their elastic-thermoplastic behaviour, from the state-of-the-art, i.e. from European Printed Publication 0 707 016 A1 mentioned in the introductory part to the Description. This being so, the polymers prepared according to the invention are particularly suited for the manufacture of articles of relatively good deformation resistance, such as e. g. sheathings for household appliances. Furthermore, it is worth mentioning that the polymers can be used in polymer mixtures for impact resistance modification. Due to their elastic characteristics, the polymers are especially suited for elastic sheets, moulded bodies, and gaskets.

The present invention will, hereinafter, be explained in more detail on the basis of several preparation examples of the catalysts and on the basis of polymerisation examples. Herewith, there show:

Fig. 1     tensile-strength measurements on two polymers prepared according to the

invention, as compared to two polymers from European Printed Publication 0 707 016 A1,

Fig. 2 an X-ray structure analysis of a metallocene complex according to the invention,

Fig. 3 a nuclear magnetic resonance (NMR) spectrum of a polymer prepared according to the invention, and

Fig. 4 a nuclear magnetic resonance (NMR) spectrum of another polymer prepared according to the invention.

Fig. 1 now illustrates the tensile-strength measurements of two selected examples from European Printed Publication 0 707 016 A1, as compared to two polymers prepared in accordance with the invention. By the remarks "Cf. Fig. 4" and "Cf. Fig. 5" in Fig. 1, the corresponding examples from European Printed Publication 0 707 016 A1 are meant in this case. As can be drawn from a comparison of those tensile-strength curves with the tensile-strength curves of the polymers (PP 36 and PP 45) prepared according to the invention, the polymers according to the invention show a distinctive, rubber-elastic plateau. Contrary thereto, the polymers according to European Printed Publication 0 707 016 A1 present either a flow behaviour (Fig. 4) or the polymer breaks in case of higher expenditures of force (Fig. 5). It is just that comparison that clearly illustrates the surprising characteristics of the polymers prepared according to the invention and showing a distinctive, rubber-elastic behaviour.

Catalyst preparation

## Obtaining of 5.6-cyclopenta-2-methyl-indane-1-one

40.4 mL of methacryl acid chloride (387.9 mmols) are, together with 62.06 gms of anhydrous aluminium chloride (20 mol% in excess), incorporated into 250 mL of  $\text{CH}_2\text{Cl}_2$ , cooled down to  $-78^\circ\text{C}$ , and slowly mixed with 50.0 mL of indane (45.84 gms, 387.9 mmols). As the indane is added, the colour changes from bright yellow to orange. The mixture is carefully quenched with diluted  $\text{HCl}$  aq, washed with hydrous  $\text{K}_2\text{CO}_3$  solution and water, and dried through  $\text{Na}_2\text{SO}_4$ .

Yield: 70.07 gms (376.2 mmols) of oily product, 97.0 % of the theory NMR (200 mcps,  $\text{CDCl}_3$  7.24 ppm):  $\delta$  1.25 ppm d ( $J = 6.9$  cps) 3 H methyl group,  $\delta$  2.10 ppm m ( $J = 3.7$  to 7.6 cps) 2 H aliphatic protons of the cycles,  $\delta$  2.62 ppm m 2 H aliphatic protons of the indanone ring,  $\delta$  2.86 ppm m ( $J = 11$  to 14 cps) 4 H aliphatic protons of the cycles,  $\delta$  3.25 ppm m ( $J = 7.0$  cps) 1 H aliphatic proton of the indanone system,  $\delta$  7.21 and 7.51 ppm s 2 H aromatic MS (GC-MS)  $m/z$  186 ( $M^+ 100\%$ ), (186, 251 mol $^{-1}$ ).

## Obtaining of 5.6-cyclopenta-2-methylindane-1-ole

70.07 gms (376.2 mmols) of the 2-methyl-5.6-cyclopentylindane-1-one are, with 5 gms of  $\text{LiAlH}_4$ , reduced in 200 mL of  $\text{Et}_2\text{O}$  by letting the ketone drip (2 hrs) slowly towards an ice-cooled suspension of  $\text{LiAlH}_4$ . Agitating is effected all through the night and quenching with  $\text{H}_2\text{O}$  is carried out, the colour of the solution changing from lime green to bright yellow. Now 15 mL of  $\text{HCl}$  are added in concentrated manner and the emulsion is agitated for 1 h. The etherial phase is separated, neutralised with 200 mL of  $\text{K}_2\text{CO}_3$  solution, and three times washed with water.

Thereafter, drying is effected through  $\text{Na}_2\text{SO}_4$  and the solvent is completely removed. A crystalline mixture of the diastereomeric 1-indanols is obtained. NMR (200 mcps,  $\text{CDCl}_3$ ):  $\delta$  1.13 ppm d 3 H methyl group,  $\delta$  1.76 ppm wide 1 H OH group,  $\delta$  2.05 ppm m 2 H aliphatic protons of the cycles,  $\delta$  2.15 to 2.71 ppm m 2 H aliphatic protons of the indanole ring,  $\delta$  2.87 ppm m 4 H aliphatic protons of the cycles,  $\delta$  3.08 ppm 1 H aliphatic proton of the indanole system,  $\delta$  4.17 and 4.93 ppm d 2 H with OH function on the indanole ring,  $\delta$  7.08 and 7.23 ppm d 2 H aromatic.

Yield: 69.62 gms, 369.8 mmols, 98.3 % of the theory  
MS (GC-MS) m/z 188 ( $M+ 100$  %), ( $188.267 \text{ gms mol}^{-1}$ ).

#### Obtaining of 5.6-cyclopenta-2-methylindene

69.62 gms (369.8 mmols) of the diastereomer mixture of the 2-methyl-5.6-cyclopentylindene-1-oles are dissolved in 500 mL of benzole; and then 3 to 5 gms of p-TosOH are added and the emulsion is, for three quarters of an hour, boiled on the water separator under reflux. The organic phase is separated, neutralised with 200 mL of  $\text{K}_2\text{CO}_3$  solution, and three times washed with water. Thereafter, drying is effected through  $\text{Na}_2\text{SO}_4$  and the solvent is completely removed.

The product colourlessly crystallises from n-pentane; yield: 57.67 gms, 338.7 mmols corresponding to 91.6 % of the theory MS (GC-MS) m/z 170 ( $M+ 100$  %), ( $170.225 \text{ gms mol}^{-1}$ ). NMR (200 mcps,  $\text{CDCl}_3$  7,24 ppm):  $\delta$  2.23 ppm m/s 5 H methylene and 2-methyl group of the indene system,  $\delta$  3.01 ppm t 4 H methylene groups,  $\delta$  3.32 ppm s 2 H methylene group acids,  $\delta$  6.51 ppm s 1 H olefinic indene system,  $\delta$  7.20 and 7.34 ppm s 2 H



aromatic, <sup>13</sup>-NMR (200 mcps, CDCl<sub>3</sub>): δ 16.8 ppm  
methyl group, δ 25.8 ppm methylene group of Cycle 5,  
δ 32.66 and 32.72 ppm methylene groups of the Cycle,  
δ 42.2 ppm methylene group of the indene system, δ  
127.1 ppm tertiary C-atom of the indene system, δ  
115.5 and 119.5 (each with H) ppm aromatic C-atoms,  
the same without H for 139.6, 141.7, 142.1, 144.4,  
and 145.0 ppm incl 4° olefinic C-atom of the indene  
system (cf. CH correlation and HH-COSY).

Obtaining of 1-(9 fluorenyl)-2(1-(5.6-cyclopenta-2-  
methyl)indenyl)ethane

3.89 gms of 2-methyl-5.6-cyclopentylindene-1 (22.85  
mmols) are, with 14.3 mL of n-BuLi, deprotonated in  
150 mL of dioxane and then mixed with a solution of  
25.13 mmols of 2-(9'-fluorenyl)ethyltrifluoromethane  
sulphonate in 100 mL of dioxane. Agitating is  
effected all through the night, heating up to 60 °C  
is carried out for half an hour and the solution is  
quenched with ca. 3 mL of H<sub>2</sub>O. The dioxane is removed  
and the product is extracted with three times 200 mL  
of Et<sub>2</sub>O. Without chromatographic processing, 6.49 gms  
(17.9 mmols, 78.3 % of the theory) of a colourless,  
crystalline Product are obtained.

NMR (200 mcps, CDCl<sub>3</sub>, 7.24 ppm): δ 1.89 ppm s 3 H  
methyl group, δ 1.41 ppm to 1.72 ppm m 4 H aliphatic  
protons of the bridge, δ 2.10 ppm pseudo-t 2 H  
aliphatic protons of the cycle, δ 2.90 ppm pseudo-t 4  
H aliphatic protons of the cycle, δ 3.87 ppm t 1 H  
aliphatic proton of the fluorene system, δ 6.40 ppm s  
1 H indene proton, δ 6.98 and 7.07 ppm aromatic pro-  
tons of the indene system, δ 7.31 to 7.77 ppm m 8 H  
aromatic of the fluorene. MS (FD) m/z 362.5 (M+ 100  
%).

Obtaining of 1-(9 fluorenyl)-2-(1-(5.6-cyclopenta-2-methyl) indenyl)ethane zirconocene dichloride

1.711 gms of 1-[1'-(2'-methyl)5', 6'-cyclopentylindenyl-2-(9"-fluorenyl)] ethane (4.72 mmols) are dissolved in 100 mL of toluol, mixed with 10 mL of dioxane, and deprotonated, at low temperature, with 5.9 mL of n-BuLi. Agitating is effected for ca. 1 hour and then the suspension is again cooled down to -78 °C. Now 1.10 gm of ZrCl<sub>4</sub> is added. That suspension is agitated, at room temperature, for another 14 hours, in which case a fine red powder forms that can be crystallised after a separation of formed LiCl from toluol.

Yield: 2.148 gms (4.11 mmols, 87.1 % of the theory).  
NMR (500 mcps, C<sub>2</sub>D<sub>2</sub>Cl<sub>4</sub> 80 °C); δ 2.00 ppm m 2 H methylene group cyclopentane ring (J = 6.8 to 7.5 cps), δ 2.15 ppm s 3 H methyl group, δ 2.79 to 2.94 ppm m 4 H methylene groups cyclopentane ring adjacent to the aromatic system (J = 7.5 to 9.7 cps), δ 4.05 ppm m (J = 3.5 to 13.2 cps) 2 H aliphatic protons of the bridge (in case of the fluorene), δ 3.83 and 4.57 ppm m (J = 4.2 to 10.0 cps) 1 H aliphatic protons of the bridge (diastereotopic) at a time, δ 6.05 ppm s 1 H indene proton, δ 7.03 to 7.85 ppm m 10 H aromatic.

MS (EI) m/z 5, 22, 6 isotopic pattern corresponding

EA CH-combustion analysis:      calculated 64.35 % C 4,  
63 % H

Found:      64.08/63.89% 4.53/4.63%

### Polymerisation example

All the polymerisations were carried out in 300 mL of toluol under the conditions indicated in Table 1.

5 The NMR data were measured by means of a Bruker AMX 500 device and evaluated on the basis of literature data.

Table 1


Run No.	Catalyst	Amount#	Tp [°C]	C3 (mol/l)	Yield [g]	tp [min]	Activity*	Tg [°C]	Tm [°C]	Mw	Mw/Mn
P 36	Flu-Et-Ind	7,5	30	2,9	36,87	33	3080	-5,9	50,2	171.000	1,96
P 45	Flu-Et-Ind	10	35	4,92	115,23	39	3603	-7,5	51,7	95.700	1,74
Run No.	Pentoden in %	mmmm	mmmr	rmrr	mmrr	mmrm + rmmr	rmrm	rrrr	rrrm	mmrm	Al/Zr
P 36		36,7	18,5	2,1	21,1	5,0	0,0	2,5	3,7	10,3	2000
P 45		36,5	17,9	1,7	21,0	5,8	0,3	3,1	3,6	10,1	2000
	#in $\mu$ mol		*kg PP/mol(Zr) mol(C3)h								

5

## Claims

1. A catalyst combination for preparing linear isotactic polymers, said catalyst combination containing a metal complex of general Formula I

10



15

wherein the substituents have the following significations:

- $R^1 - R^7$  linear or branched  $C_1$  to  $C_{10}$  alkyl, 5- to 7-linked cycloalkyl which, in its turn, can carry one or several  $C_1$  to  $C_6$  alkyl residues as substituent,  $C_6$  to  $C_{18}$  aryl or arylalkyl or alkylaryl, in which case  $R^1/R^2$ ,  $R^3/R^4$ ,  $R^5/R^6$  can be partially or simultaneously integrated into 5- to 7-linked cycloalkyl or aryl rings fused thereto;


25

- $R^9, R^{10}$   $C_1$  to  $C_8$  alkyl, 4- to 7-linked cycloalkyl, aryl, in which case  $R^9, R^{10}$  can, jointly with E, form a 4- to 7-linked cycloalkyl or aryl;
- 5  $R^{11}$   $C_1$  to  $C_8$  alkyl, aryl,  $C_1$  to  $C_8$  oxyalkyl,  $C_1$  to  $C_8$  trialkylsiloxyl;
- $M$  titanium, zirconium, hafnium, vanadium, niobium, tantalum;
- 10  $X$  halogen or  $C_1$  to  $C_8$  alkyl, aryl, benzyl;
- $E$  carbon, silicon, germanium or 1,2-ethyl, 1,3-propyl, 1,4-butyl;

and an activator.


- 15 2. A catalyst combination as well as an activator according to Claim 1, characterised in that the activator is an open-chain or cyclic alumoxane compound of general Formula II or III

20




25

$R^8$  standing for a  $C_1$  to  $C_8$  alkyl group and  $n$  standing for a number between 5 and 30, and/or a cationic activator of general Formulas IV to VI



$R^9$  signifying a  $C_1$  to  $C_4$  alkyl group or an aryl group.

3. A catalyst combination according to Claim 1 or 2, characterised in that the metal complex according to general Formula I is a compound of general Formula VII



wherein the residues  $R^1$  to  $R^{11}$  have the significations indicated in general Formula I and  $E^2 = CH_2, O$  or  $S$  and  $n = 1$  or  $2$ .

4. A catalyst combination according to at least one of Claims 1 to 3, characterised in that the metallocene complex of general Formula I and the activator according to general Formulas II to VI are utilised in such quantities that the atomic ratio between aluminium from the alumoxane and/or boron from the cationic activator and the transition metal from the metallocene complex is within the range of from 1:1 to  $10^6$ :1.

5. A process for preparing linear, isotactic polymers which have a structure of which the

5           tacticity varies within the range of between 25  
and 60 % of [mmmm] pentad concentration, an  
arbitrary or rather regular sequence of  
isotactic and atactic blocks being excluded, in  
which process a C<sub>2</sub> to C<sub>10</sub> olefin are reacted with  
a catalyst combination being defined in claim 1  
to 4.

10           6. A process according to Claim 5, characterised in  
that the polymerisation reaction is carried out  
in the gas phase, in suspension or in  
supercritical monomers, especially in solvents  
inert under the polymerisation conditions.

15           7. A process according to claim 5 or 6,  
characterised in that, as inert solvents,  
solvents are used that do not contain any  
reactive molecules, such as e.g. benzole,  
toluol, xylol, ethyl benzole or alkanes such as  
20           e.g. propane, n-butane, i-butane, pentane,  
hexane, heptane or mixtures thereof.

25           8. A process according to at least one of Claims 5  
to 7, characterised in that polymerisation is  
carried out at pressures of from 1 to 100 bars,  
preferably from 3 to 20 bars and especially from  
5 to 15 bars, and at temperatures of from - 50  
to 200 °C, of preference from 10 to 150 °C and  
especially at from 20 to 40 °C.



FIG.1







FIG.2







# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP 99/02378

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C08F4/64 C08F10/06

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	DIETRICH, ULF ET AL: "Control of Stereoerror Formation with High-Activity "Dual-Side" Zirconocene Catalysts: A Novel Strategy To Design the Properties of Thermoplastic Elastic Polypropenes" J. AM. CHEM. SOC. (1999), 121(18), 4348-4355, XP002110148 page 4349, compound 15 page 4351, table 2 page 4354	1-8
P,X	RIEGER, BERNHARD ET AL: "Novel metallocene catalyzed polypropene homo- and brush-copolymers: control of new morphologies and beyond" POLYM. MATER. SCI. ENG. (1999), 80, 51-52, XP002110149 the whole document	1-3,5

-/--

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "Δ" document member of the same patent family

Date of the actual completion of the international search

29 July 1999

Date of mailing of the international search report

17/09/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Gamb, V

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 99/02378

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	DIETRICH U ET AL: "NEW CLASS OF THERMOPLASTIC ELASTIC POLYPROPENES PREPARED WITH A HIGH ACTIVITY 'DUAL SIDE' ZIRCONOCENE CATALYST" RAPRA ABSTRACTS, vol. 36, no. 1, January 1999 (1999-01), page 138 XP000800737 ISSN: 0033-6750 abstract	1-3
A	RIEGER B: "STEREOSPECIFIC PROPENE POLYMERIZATION WITH RAC- 1,2-BIS(N5-(90FLUORENYL))-1-PHENYLETHANEZIRCONIUM DICHLORIDE/METHYLALUMOXANE" POLYMER BULLETIN, vol. 32, no. 1, 1 January 1994 (1994-01-01), pages 41-46, XP000420835 ISSN: 0170-0839 page 43 page 45; examples 3,5; table 2	1-8
A	GB 2 241 244 A (CHIEN JAMES C W ; RAUSCH MARVIN D (US); ACADEMY OF APPLIED SCIENCES) 28 August 1991 (1991-08-28) abstract page 6	1
A	EP 0 582 194 A (HOECHST AG) 9 February 1994 (1994-02-09) page 17; example 5	1

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/02378

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2241244 A	28-08-1991	US 5756614 A	26-05-1998
EP 0582194 A	09-02-1994	AT 165832 T	15-05-1998
		DE 59308494 D	10-06-1998
		ES 2114978 T	16-06-1998
		JP 6157661 A	07-06-1994
		US 5455365 A	03-10-1995
		US 5869584 A	09-02-1999